



ARMORVIN TOTAL PU OIL TPHF 912873



Hose totally made of PU with steel spiral reinforcement for suction and delivery of abrasive materials, liquids, oils and fatty food stuffs.

DETAILS

	SMOOTH SURFACE	* * * * *
	FLEXIBILITY	* *
	ABRASION RESISTANCE	* * *
	TEMPERATURE RANGE	-25 °C 90 °C
	CHEMICAL RESISTANCE	PU Table
	CRUSHING RESISTANCE	* * *
	FOR FOOD	EU according to Declaration of Conformity. FDA according to Declaration of Conformity
	O-PHTALATE FREE	* * * * *
	PHTALATE FREE	* * * * *

Ø nominal mm	Ø nominal inch	Ø i.d. mm	Ø o.d. mm	vacuum 23 °C m/H ₂ O	working press. at 23 °C r.1:3 bar	bursting press. at 23 °C bar	bending radius mm	total thickness mm	Ø steel wire mm	spiral pitch mm	spiral direction	weight meter g/m	coil length m	Availability
20		20.5	28.5	9	7	21	80	4	1	7.5	right	410	30	In stock
25	1	25.3	33.5	9	7	21	100	4.1	1	7.5	right	520	30	In stock
30		30	38.8	9	7	21	120	4.4	1	8	right	620	30	In stock
32	1 1/4	32.1	40.9	8	6	18	130	4.4	1	7.5	right	660	30	In stock
35		35.2	43.6	8	6	18	135	4.2	1.2	8.5	right	750	30	On demand
38	1 1/2	38.1	46.7	8	6	18	140	4.3	1.2	8.5	right	800	30	In stock
40		40.5	49.9	8	6	18	160	4.7	1.2	8	right	900	30	In stock
45	1 3/4	45.2	54	8	6	18	180	4.4	1.5	9.5	right	1040	30	On demand
50	2	51	60,4	8	6	18	200	4.7	1.5	9.5	right	1160	30	In stock
60		60	70	8	6	18	240	5	1.5	10.5	right	1440	30	In stock
63	2 1/2	63	73.4	8	5	15	280	5.2	1.5	10.5	right	1560	30	On demand
70		70.4	80	8	5	15	300	4.8	1.8	12,5	right	1650	30	In stock
75		75.4	85.2	7	5	15	320	4.9	1.8	12.5	right	1730	30	In stock
76	3	76	86	7	5	15	330	5	1.8	12.5	right	1750	30	On demand
80		80	90	7	4	12	340	5	1.8	13	right	1860	30	In stock
100		101	114.4	7	3	9	400	6.7	2.5	15	right	3350	30	On demand
102	4	102	116	7	3	9	420	7	2.5	15	right		30	On demand

All technical specifications apply to a temperature of 23° C ± 2° C (ISO 291)

The tolerance on all specifications ±5% (Tolerance Percentage is applicable on ALL DATA across our range)